

## Inspection Certificate

Abnahmeprüfungszeugnis DIN EN 10204.3.1

Certificat De reception

Certificado di collaudo

Keuringsrapport



Batch Number	2206002	Product Name	Zyglo ZL-2C Fluorescent Penetrant
Date of Manufacture	23/06/2022	B.B.E.	06/2027

### Specification: Specification

We hereby certify that when tested at the time of manufacture, the above material:

1. Meets the requirements of and has been tested for sulfur and halogens according to:

a) ASME Boiler and Pressure Vessel Code, 2019 Edition, Section V, Non-destructive Examination.

b) Anion analysis by ASTM D129 decomposition followed by Ion Chromatography method Annex A4.

c) ASTM E-165/E-165M-18, Paragraph 7.1.

d) MIL-STD-2132E, March 29, 2016, Paragraph 6.1.3.

2. Meets the requirements of Rolls Royce RRP 58003 (CSS 232), SAFRAN Pr 5000 / In 5000B, AMS 2644H and ASTM E1417/E 1417M-21 Paragraph 5.1 & 6.5.1.

Penetrant brightness tested according to ASTM E 1135.

3. We further certify that the material does not contain mercury as a basic element and no mercury bearing equipment was used in its manufacture.

Test	Section	Limit	Result
Specification			Passed

### Specification: Ion Testing Results

Test results obtained were as follows:

Test	Section	Limit	Result
Sulphur Content			116 ppm
Halogen Content			53 ppm

### Specification: AMS 2644H Penetrant Test Results

When sampled and tested according to paragraph 4.3.2 section 4.2.2.1 of AMS 2644H the following results were obtained:

Test	Section	Limit	Result
Flashpoint (SMT 14)	3.3.3		109.5 °C
Viscosity	3.3.4		5.81 mm <sup>2</sup> /s (cSt)
Fluorescent Brightness	3.3.8.3.2		80.37 %
Penetrant Removal	3.3.8.6		Passed
Water Content (SMT 18)	3.3.8.7		0.02 %

### Specification: Pratt & Whitney Aircraft Results

VENDOR'S REPORT - TEST RESULTS

REPORTS, MATERIALS CONTROL LABORATORY

PRATT & WHITNEY AIRCRAFT

(Plant to which material is shipped)

This is to certify that paragraph number 1 + 5 apply to the shipment described below (Insert at least one of the first 4, plus 5 if applicable)

1. (Applicable to all raw material, to parts made from raw material furnished or purchased by vendor, or to assemblies of which some or all components are made from raw materials furnished or purchased by vendor) Material, parts, or components of assemblies have been inspected & accepted to the specifications involved, & results of tests required by PWA are as shown herein.

2. (Applicable to parts or assembly components made from raw material furnished by PWA and not chemically or metallurgically treated by vendor so as to change surface or internal condition significantly) Parts or assemblies have been machined or formed from material furnished by PWA to make these parts or components of assemblies.

3. (Applicable to parts or assembly components made from raw material furnished by PWA and chemically or metallurgically treated by vendor so as to change surface or internal condition significantly) Parts or components of assemblies have been made from raw material furnished by PWA to make these parts or components of assemblies. Parts, components of assemblies, or assemblies have been inspected and accepted to the

## Inspection Certificate

Abnahmeprüfungszeugnis DIN EN 10204.3.1

Certificat De reception

Certificado di collaudo

Keuringsrapport



specifications involved, and results of tests required by PWA are as shown herein.

4. (Applicable to repaired or reworked raw material, parts or assemblies) The raw material, parts or assemblies have been reworked or repaired in accordance with PWA instructions, and are the same material, parts or assemblies returned for such reworking or repair, except for replacement of assembly components, in which case paragraphs 1 & 5 are also applicable.

5. (Applicable to all assemblies, and to parts when specifically, authorised by purchaser) Results of all chemical and physical tests not shown below as well as all other evidence which shows acceptability of raw materials & assembly components, are on file and available for inspection at any reasonable time.

PART OR ASS'yNO (Size if no part no): PMC 4352-2

CHG.LTR:

SPECIFICATION AS ORDERED \* PWA 300 Rev.

QUANTITY:

DATE SHIPPED:

QUANTITY:

DATE SHIPPED:

LOCATION OF PWA PLANT SHIPPED TO:

PACK SUB NO:

PO NO:

HEAT, LOT, CODE or BATCH NO: As listed above

RAW MATERIAL VENDOR:

TYPE COMPOUND or CASTING: ZL-2C Penetrant

PWA HEAT CODES:

\* If material, parts or assemblies do not entirely conform to specification requirements, the deviation and authority for furnishing such material are indicated below:

Magnaflux certifies that ZL-2C meets the requirements of PMC 4352-2

Test	Section	Limit	Result
Flashpoint (SMT 14)		93°C Minimum	109.5 °C
Viscosity		5.60 - 7.28 mm <sup>2</sup> /s (cSt) @38°C	5.81 mm <sup>2</sup> /s (cSt)
Water Content (SMT 18)			0.02 %
Fluorescent Brightness		>80%	80.37 %
Separation of Constituents - Homogenous		None	Passed
Fluoride Content		≤ 50 ppm	<1 ppm
Chloride Content		≤ 400 ppm	53 ppm
Sulphur Content		≤ 1000 ppm	116 ppm
Sodium (SMT 44)		≤ 0.010 %	0.0006 %

--- EOR ---

### Notes:

1. Our batch number appears on the label of bulk containers. Aerosols have batch numbers printed on bottom of the container. Bulk materials have a minimum shelf life of 5 years from date of manufacture. Aerosols have a minimum shelf life of 3 years from date of manufacture.
2. Most specifications require test results stated in percent, but some require parts per million (ppm). To convert "percent" figures to "parts per million" move the decimal four places to the right.
3. MIL-STD-271, MIL-STD-2132 and ASME Sec V, all require that materials be subject to a procedure to evaporate off volatile solvents before analysis for Sulfur and Halogens. According to these specifications, only those residues higher than 0.005 g/100ml shall be analysed for Sulfur and Halogens. Lower residues shall be reported.
4. The above certification gives the results obtained at the time of manufacture. Age and use may alter the properties of any material.

**Magnaflux** (A Division of ITW Ltd),  
Faraday Road, South Dorcan Industrial Estate,  
Swindon, Wiltshire, SN3 5HE, UK  
Tel: +44 (0)1793 524566  
Fax: +44 (0)1793 490459  
Email: sales.eu@magnaflux.com  
www.magnaflux.eu