

## Inspection Certificate

Abnahmeprüfungszeugnis DIN EN 10204.3.1  
Certificat De reception  
Certificado di collaudo  
Keuringsrapport



<b>Batch Number</b>	<b>2406026</b>	<b>Product Name</b>	Zyglo ZP-4D Dry Developer
<b>Date of Manufacture</b>	27/06/2024	<b>B.B.E.</b>	06/2029

### Specification: Specification

We hereby certify that when tested at the time of manufacture, the above material:

1. Meets the requirements of and has been tested for sulphur and halogens according to:
  - a) ASME Boiler and Pressure Vessel Code, 2023 Edition, Section V, Non-destructive Examination.
  - b) ASTM E-165/E-165M-18, Paragraph 7.1.
  - c) MIL-STD-2132E, March 29, 2016, Paragraph 6.1.3.
  - d) SAFRAN Pr 5000D

### Specification

### Specification: Ion Test Results

Test results obtained were as follows:

Test	Section	Limit	Result
Sulphur Content		<200ppm	47ppm
Halogen Content		<350ppm	142ppm

### Specification: AMS 2644H Developer Results

When sampled according to paragraph 4.3.2 section 4.2.2.3 of AMS 2644H the following results were obtained:

Test	Section	Limit	Result
Developer Fluorescence	3.3.10.2		Passed
Developer Removability	3.3.10.4		Passed

### Specification: Pratt & Whitney Aircraft Results

VENDOR'S REPORT - TEST RESULTS

REPORTS, MATERIALS CONTROL LABORATORY  
PRATT & WHITNEY AIRCRAFT  
(Plant to which material is shipped)

This is to certify that paragraph number 1 + 5 apply to the shipment described below (Insert at least one of the first 4, plus 5 if applicable)

1. (Applicable to all raw material, to parts made from raw material furnished or purchased by vendor, or to assemblies of which some or all components are made from raw materials furnished or purchased by vendor) Material, parts, or components of assemblies have been inspected & accepted to the specifications involved, & results of tests required by PWA are as shown herein.
2. (Applicable to parts or assembly components made from raw material furnished by PWA and not chemically or metallurgically treated by vendor so as to change surface or internal condition significantly) Parts or assemblies have been machined or formed from material furnished by PWA to make these parts or components of assemblies.
3. (Applicable to parts or assembly components made from raw material furnished by PWA and chemically or metallurgically treated by vendor so as to change surface or internal condition significantly) Parts or components of assemblies have been made from raw material furnished by PWA to make these parts or components of assemblies. Parts, components of assemblies, or assemblies have been inspected and accepted to the specifications involved, and results of tests required by PWA are as shown herein.
4. (Applicable to repaired or reworked raw material, parts or assemblies) The raw material, parts or assemblies have been reworked or repaired in accordance with PWA instructions, and are the same material, parts or assemblies returned for such reworking or repair, except for replacement of assembly components, in which case paragraphs 1 & 5 are also applicable.
5. (Applicable to all assemblies, and to parts when specifically, authorised by purchaser) Results of all chemical and physical tests not shown below as well as all other evidence which shows acceptability of raw materials & assembly components, are on file and available for inspection at any reasonable time.

PART OR ASS'yNO (Size if no part no): PMC 4356-4  
CHG.LTR:  
SPECIFICATION AS ORDERED \* PWA 300 Rev. BU

**Inspection Certificate**

Abnahmeprüfungszeugnis DIN EN 10204.3.1  
Certificat De reception  
Certificado di collaudo  
Keuringsrapport



QUANTITY:  
DATE SHIPPED:  
QUANTITY:  
DATE SHIPPED:  
LOCATION OF PWA PLANT SHIPPED TO:  
PACK SUB NO:  
PO NO:  
HEAT, LOT, CODE or BATCH NO: As listed above  
RAW MATERIAL VENDOR:  
TYPE COMPOUND or CASTING: ZP-4D Developer  
PWA HEAT CODES:

\* If material, parts or assemblies do not entirely conform to specification requirements, the deviation and authority for furnishing such material are indicated below:

Magnaflux certifies that ZP-4D meets the requirements of PMC 4356-4

Test	Section	Limit	Result
Appearance		White fluffy powder	Passed
Purity		No yellow, red or green fluorescence	Passed
Fluoride Content		≤ 50 ppm	<10ppm
Chloride Content		≤ 1000 ppm	132ppm
Sodium (SMT 44)		≤ 0.100 %	0.0008%
Sulphur Content		≤ 1000 ppm	47ppm

--- EOR ---

**Prepared by**

**Approved by**

**Notes:**

1. Our batch number appears on the label of bulk containers. Aerosols have batch numbers printed on bottom of the container.
2. Most specifications require test results stated in percent, but some require parts per million (ppm). To convert "percent" figures to "parts per million" move the decimal four places to the right.
3. MIL-STD-271, MIL-STD-2132 and ASME Sec V, all require that materials be subject to a procedure to evaporate off volatile solvents before analysis for Sulfur and Halogens. According to these specifications, only those residues higher than 0.005 g/100ml shall be analysed for Sulfur and Halogens. Lower residues shall be reported.
4. The above certification gives the results obtained at the time of manufacture. Age and use may alter the properties of any material.