

Batch Number	2410029	Product Name	Zyglo ZL-67B Water Washable Fluorescent Penetrant
Date of Manufacture	10/10/2024	B.B.E.	10/2029

## **Specification: Specification**

We hereby certify that when tested at the time of manufacture, the above material: 1. Meets the requirements of and has been tested for sulfur and halogens according to: a) ASME Boiler and Pressure Vessel Code, 2023 Edition, Section V, Non-destructive Examination.

b) ASTM E-165/E-165M-18, Paragraph 7.1.

c) MIL-STD-2132E, March 29, 2016, Paragraph 6.1.3.

d) EN ISO 3452-2

2. Meets the requirements of Rolls Royce RRP 58003 (CSS 232), SAFRAN Pr 5000 / In 5000D, AMS 2644J and ASTM E 1417/E 1417M-21 Paragraph 5.1 & 6.5.1.

Penetrant brightness tested according to ASTM E 1135.

3. We further certify that the material does not contain mercury as a basic element and no mercury bearing equipment was used in its manufacture.

Test	Section	Limit	Result	
Specification			Passed	

# **Specification: Ion Testing Results**

Test results obtained were as follows:

Test	 Limit	Result
Sulphur Content		18 ppm
Halogen Content		35 ppm

## Specification: AMS 2644J Penetrant Test Results

Type 1 Method A Level 3 Penetrant.

When sampled and tested according to paragraph 4.3.2 section 4.2.2.1 of AMS 2644J the following results were obtained:

Test	Section Limit	Result
Flashpoint (SMT 14)	3.3.3	116.5 °C
Fluorescent Brightness	3.3.8.3.2	101 %
Water Tolerance (SMT 2)	3.3.8.5	30 %
Penetrant Removal	3.3.8.6	Passed
Water Content (SMT 18)	3.3.8.7	0.34 %
Viscosity	3.3.4	22.40 mm2/s (cSt)

#### **Specification: Pratt & Whitney Aircraft Results**

VENDOR'S REPORT - TEST RESULTS

REPORTS, MATERIALS CONTROL LABORATORY PRATT & WHITNEY AIRCRAFT (Plant to which material is shipped)

This is to certify that paragraph number 1 + 5 apply to the shipment described below (Insert at least one of the first 4, plus 5 if applicable)

1. (Applicable to all raw material, to parts made from raw material furnished or purchased by vendor, or to assemblies of which some or all components are made from raw materials furnished or purchased by vendor) Material, parts, or components of assemblies have been inspected & accepted to the specifications involved, & results of tests required by PWA are as shown herein.

2. (Applicable to parts or assembly components made from raw material furnished by PWA and not chemically or metallurgically treated by vendor so as to change surface or internal condition significantly) Parts or assemblies have been machined or formed from material furnished by PWA to make these parts or components of assemblies.

3. (Applicable to parts or assembly components made from raw material furnished by PWA and chemically or metallurgically treated by vendor so as to change surface or internal condition significantly) Parts or components of assemblies have been made from raw material furnished by PWA to



make these parts or components of assemblies. Parts, components of assemblies, or assemblies have been inspected and accepted to the specifications involved, and results of tests required by PWA are as shown herein.

4. (Applicable to repaired or reworked raw material, parts or assemblies) The raw material, parts or assemblies have been reworked or repaired in accordance with PWA instructions, and are the same material, parts or assemblies returned for such reworking or repair, except for replacement of assembly components, in which case paragraphs 1 & 5 are also applicable.

5. (Applicable to all assemblies, and to parts when specifically, authorised by purchaser) Results of all chemical and physical tests not shown below as well as all other evidence which shows acceptability of raw materials & assembly components, are on file and available for inspection at any reasonable time.

PART OR ASS'yNO (Size if no part no): PMC 4360-10 CHG.LTR: SPECIFICATION AS ORDERED \* PWA 300 Rev. BU QUANTITY: DATE SHIPPED: QUANTITY: DATE SHIPPED: LOCATION OF PWA PLANT SHIPPED TO: PACK SUB NO: PO NO: HEAT, LOT, CODE or BATCH NO: As listed above RAW MATERIAL VENDOR: TYPE COMPOUND or CASTING: ZL-67B Penetrant PWA HEAT CODES:

\* If material, parts or assemblies do not entirely conform to specification requirements, the deviation and authority for furnishing such material are indicated below:

Magnaflux certifies that ZL-67B meets the requirements of PMC 4360-10.

Test	Section	Limit	Result
Separation of Constituents - Homogenous		Pass	Passed
Fluoride Content		≤ 50 ppm	1 ppm
Chloride Content		≤ 400 ppm	34 ppm
Sodium (SMT 44)		≤ 100 ppm	8 ppm
Flashpoint (SMT 14)		>93°C	116.5 °C
Sulphur Content		≤ 1000 ppm	18 ppm
Fluorescent Brightness		>90%	101 %
Water Content (SMT 18)		<1%	0.34 %
Viscosity		20.07 - 24.53 mm2/s (cSt) @ 38℃	22.40 mm2/s (cSt)

--- EOR ---

Prepared by

Approved by

Leinof

#### Notes:

1. Our batch number appears on the label of bulk containers. Aerosols have batch numbers printed on bottom of the container.

2. Most specifications require test results stated in percent, but some require parts per million (ppm). To convert "percent" figures to "parts per million" move the decimal four places to the right.

3. MIL-STD-271, MIL-STD-2132 and ASME Sec V, all require that materials be subject to a procedure to evaporate off volatile solvents before analysis for Sulfur and Halogens. According to these specifications, only those residues higher than 0.005 g/100ml shall be analysed for Sulfur and Halogens. Lower residues shall be reported.

4. The above certification gives the results obtained at the time of manufacture. Age and use may alter the properties of any material.

Magnaflux (A Division of ITW Ltd), Faraday Road, South Dorcan Industrial Estate, Swindon, Wilshire, SN3 5HE, UK Tel: +44 (0)1793 524566 Fax: +44 (0)1793 490459 Email: sales eu@magnaflux.com www.magnaflux.eu