

Inspection Certificate

Abnahmeprüfungszeugnis DIN EN 10204.3.1

Certificat De reception

Certificado di collaudo

Keuringsrapport



Batch Number	2502019	Product Name	Zyglo ZL-60D Water Washable Fluorescent Penetrant
Date of Manufacture	05/02/2025	B.B.E.	02/2030

Specification: Specification

We hereby certify that when tested at the time of manufacture, the above material:

1. Meets the requirements of and has been tested for sulfur and halogens according to:

a) ASME Boiler and Pressure Vessel Code, 2023 Edition, Section V, Non-destructive Examination.

b) ASTM E-165/E-165M-23, Paragraph 7.1.

c) MIL-STD-2132E, March 29, 2016, Paragraph 6.1.3.

2. Meets the requirements of Rolls Royce RRP 58003 (CSS 232), AMS 2644J, EN ISO 3452-2 and ASTM E 1417/E 1417M-21 EDT1 Paragraph 5.1& 6.5.1.

Penetrant brightness tested according to ASTM E 1135.

3. We further certify that the material does not contain mercury as a basic element and no mercury bearing equipment was used in its manufacture.

Test	Section	Limit	Result
Specification			Passed

Specification: Ion Testing Results

Test results obtained were as follows:

Test	Section	Limit	Result
Sulphur Content (S)			0.0010%
Halogen Content (F + Cl)			0.0057%

Specification: AMS 2644 Test results

Type 1 Level 2 Penetrant

Meets the requirements of Rolls Royce RRP 58003 (CSS 232), SAFRAN Pr 5000 / In 5000D, AMS 2644J and ASTM E 1417/E 1417M-16 Paragraph 5.1& 6.5.1.

Penetrant brightness tested according to ASTM E 1135.

When tested according to paragraph 4.3.2 of AMS 2644J the following results were obtained:

Test	Section	Limit	Result
Flashpoint (SMT 14)	3.3.3	93°C Min	108 °C
Kinematic Viscosity (SMT 17)	3.3.4	8.81 - 11.91 cS	11.16cS
Fluorescent Brightness	3.3.8.3.2	Minimum 80%	96%
Water Tolerance (SMT 2)	3.3.8.5	5.0% Minimum	28.23%
Removability	3.3.8.6	Equal to or less than standard	Passed
Water Content (SMT 18)	3.3.8.7	1.0% Max	0.20%

Specification: Pratt & Whitney Test Results

This is to certify that paragraph number 1 + 5 apply to the shipment described below (Insert at least one of the first 4, plus 5 if applicable)

1. (Applicable to all raw material, to parts made from raw material furnished or purchased by vendor, or to assemblies of which some or all components are made from raw materials furnished or purchased by vendor) Material, parts, or components of assemblies have been inspected & accepted to the specifications involved, & results of tests required by PWA are as shown herein.

2. (Applicable to parts or assembly components made from raw material furnished by PWA and not chemically or metallurgically treated by vendor so as to change surface or internal condition significantly) Parts or assemblies have been machined or formed from material furnished by PWA to make these parts or components of assemblies.

3. (Applicable to parts or assembly components made from raw material furnished by PWA and chemically or metallurgically treated by vendor to change surface or internal condition significantly) Parts or components of assemblies have been made from raw material furnished by PWA to make these parts or components of assemblies. Parts, components of assemblies, or assemblies have been inspected and accepted to the specifications

Inspection Certificate

Abnahmeprüfungszeugnis DIN EN 10204.3.1

Certificat De reception

Certificado di collaudo

Keuringsrapport



involved, and results of tests required by PWA are as shown herein.

4. (Applicable to repaired or reworked raw material, parts or assemblies) The raw material, parts or assemblies have been reworked or repaired in accordance with PWA instructions, and are the same material, parts or assemblies returned for such reworking or repair, except for replacement of assembly components, in which case paragraphs 1 & 5 are also applicable.

5. (Applicable to all assemblies, and to parts when specifically, authorised by purchaser) Results of all chemical and physical tests not shown below as well as all other evidence which shows acceptability of raw materials & assembly components, are on file and available for inspection at any reasonable time.

Part or Ass'y No (Size if no Part no) : PMC-4350-11

Chg Ltr:

Sur no:

Specification as ordered: PWA300 Rev BV

Quantity:

Date Shipped:

Location of PWA Plant Shipped to:

Pack Sub No:

PO No:

Heat/Lot/Code or Batch No: As stated above

Raw Material Vendor:

Type Compound or Casting: ZL-60D Penetrant

PAW Heat Code:

Test	Section	Limit	Result
Chloride Content		</=400ppm	55ppm
Fluoride Content		</=50 ppm	2ppm
Sulphur Content (S)		</=1000ppm	10ppm
Sodium (SMT 44)		</=100ppm	44.5ppm
Kinematic Viscosity (SMT 17)		8.81 - 11.91 cS @38°C	11.16cS
Flashpoint (SMT 14)		93°C Minimum	108 °C
Fluorescent Brightness		Minimum 80%	96%
Separation of Constituents - Homogenous		None	Passed
Water Content (SMT 18)		<1%	0.20%

--- EOR ---

Inspection Certificate

Abnahmeprüfungszeugnis DIN EN 10204.3.1

Certificat De reception

Certificado di collaudo

Keuringsrapport



Prepared by

A handwritten signature in black ink, appearing to read 'Zaino'.

Approved by

A handwritten signature in black ink, consisting of stylized initials followed by a horizontal line.

Notes:

1. Our batch number appears on the label of bulk containers. Aerosols have batch numbers printed on bottom of the container.
2. Most specifications require test results stated in percent, but some require parts per million (ppm). To convert "percent" figures to "parts per million" move the decimal four places to the right.
3. MIL-STD-271, MIL-STD-2132 and ASME Sec V, all require that materials be subject to a procedure to evaporate off volatile solvents before analysis for Sulfur and Halogens. According to these specifications, only those residues higher than 0.005 g/100ml shall be analysed for Sulfur and Halogens. Lower residues shall be reported.
4. The above certification gives the results obtained at the time of manufacture. Age and use may alter the properties of any material.

FORMAT: MX 101.137 MC-09 Rev 31

Magnaflux (A Division of ITW Ltd),
Faraday Road, South Dorcan Industrial Estate,
Swindon, Wiltshire, SN3 5HE, UK
Tel: +44 (0)1793 524566
Fax: +44 (0)1793 490459
Email: sales.eu@magnaflux.com
www.magnaflux.eu