Inspection Certificate
Abnahmeprüfungszeugnis DIN EN 10204.3.1
Certificat De reception
Certificado di collaudo
Keuringsrapport

Batch Number	**261007**	**Product Name**	Magnaglo 14HF Oil Based Fluorescent MPI Ink Aerosol
Date of Manufacture	08/10/2026 13/10/2026	**B.B.E.**	10/2031

Specification: Specification

We hereby certify that the above Magnetic Particle Inspection Material meets the requirements of Aerospace Material specification AMS-3045F, Magnetic Particles, Fluorescent, Wet method, Oil vehicle.
We further certify that the above Magnetic Particle Inspection Material meets the requirements of the following specifications:

A. (For Aerosols only) AMS-3046J.

B. ASME Boiler and Pressure Vessel Code, 2025 Edition, Section V, Non-destructive Examination.

C. ASTM E 709-21, Paragraphs 8.1.2, 8.2, 8.3, 8.5, 8.5.3 & 8.5.4.1.

D. ASTM E1444/E1444M-26, Paragraphs 5.5.2 and 5.5.3.

E. AMS 2641D Type 1 Oil vehicle. Flash point greater then 93°C.

F. Rolls Royce RRP 58004 (CSS 231).

G. SNECMA DMR70-520.

H. SAFRAN In-5300.

I. AMS 3044H (Magnetic particles used in the product).

We further certify that this material does not contain mercury as a basic element and no mercury bearing equipment was used in its manufacture.

Test	Section	Limit	Result
Specification			Passed

Specification: AMS-3045G test results

We hereby certify that the above Magnetic Particle Inspection Material meets the requirements of Aerospace Material specification AMS-3045G, Magnetic Particles, Fluorescent, Wet method, Oil vehicle.

Test	Section	Limit	Result
Contamination	3.3.1	No foreign material, scum or agglomeration	Passed
Concentration	3.3.2	0.1 - 0.4 mL magnetic particles per 100mL	0.22mL
Sensitivity-Ketos Ring Indications (SMT 24)	3.3.3	7 Hole indications shown	7 indications
Colour		Fluorescence : Yellow Green	Passed

Specification: EN ISO 9934-2

When tested at the time of manufacture the following results were obtained. The information is derived from our quality checks. It does not relive the purchaser from examining the proodct upon delivery and gives no assurance of the product for any particular purpose.

Test	Section	Limit	Result
Performance Reference block 1	7.1	Indication on Reference Block 1 (#072814)	Passed
Performance Reference block 2	7.1	Total length of indication on Reference Block 2	9cm
Colour	7.2	Light Brown Liquid	Passed
Particle Size - dl (SMT 41)	7.3	Report	7.61 um
Particle Size - da (SMT 41)	7.3	Report	4.96 um
Particle Size - du (SMT 41)	7.3	Report	11.31 um
Fluorescent Co-Efficient	7.5	Shall be within 10% of the type testing	108.66%
Fluorescence of Carrier Fluid	7.6	Not brighter than quinine sulphate solution	Passed
Flashpoint (SMT 14)	7.7	Report	100.5°C

Viscosity	7.9	Less than 5mPa s at 20°C	2.82 mPa s at 20°C
Mechanical Short Term Stability	7.10	No decrease in sensitivity after test	Passed
Foaming		No significant foaming	Passed
Storage Stability	7.13	5 Years	Passed

--- EOR ---

Prepared by **Approved by**



Notes:
1. Our batch number appears on the label of bulk containers. Aerosols have batch numbers printed on bottom of the container.
2. Most specifications require test results stated in percent, but some require parts per million (ppm). To convert "percent" figures to "parts per million" move the decimal four places to the right.
3. MIL-STD-271, MIL-STD-2132 and ASME Sec V, all require that materials be subject to a procedure to evaporate off volatile solvents before analysis for Sulfur and Halogens. According to these specifications, only those residues higher than 0.005 g/100ml shall be analysed for Sulfur and Halogens. Lower residues shall be reported.
4. The above certification gives the results obtained at the time of manufacture. Age and use may alter the properties of any material.

Magnaflux (A Division of ITW Ltd),
Faraday Road, South Dorcan Industrial Estate,
Swindon, Wiltshire, SN3 5HE, UK
Tel: +44 (0)1793 524566
Fax: +44 (0)1793 490459
Email: sales.eu@magnaflux.com
www.magnaflux.eu